

# TRAIN • B9223

LIST OF PROPERTIES		B9223
<b>MATERIAL COMPOSITION</b>		
<b>FABRIC</b>		100 % PES / 1100 DTEX
<b>TOTAL WEIGHT</b>	DIN EN ISO 2286/2 1998	850 G/M <sup>2</sup>
<b>CHARACTERISTICS</b>		AB
<b>LACQUERING</b>	DIN EN ISO 2286/2 1998	1/1
<b>EMBOSSING</b>	DIN EN ISO 2286/2 1998	GLOSSY
<b>BREAKING STRENGTH WARP</b>	EN ISO 1421/1 1998	3000 N / 5 CM
<b>BREAKING STRENGTH WEFT</b>	EN ISO 1421/1 1998	3000 N / 5 CM
<b>TEAR STRENGTH WARP</b>	DIN 53363 2003	300 N
<b>TEAR STRENGTH WEFT</b>	DIN 53363 2003	300 N
<b>ADHESION</b>	EN ISO 2411 2000	125 N / 5 CM
<b>TEMPERATURE RESISTANCE</b>	DIN EN 1876/2 1998	-30/+80 °C
<b>LIGHT FASTNESS (EXCEPT WHITE AND (HALF-)TRANSPARENT)</b>	ISO 105 B02 1988	> 6
<b>FIRE BEHAVIOR</b>	DIN 4102 1981	B1
<b>APPLICATION</b>		RAILWAY / TILT / REGULAR (DB)
<b>TD HAUBENDACH-PLANEN REV.07/2009</b>		CONFORM

All our technical characteristics are indicative