

CAMPING • C2349

LIST OF PROPERTIES		
		C2349
MATERIAL COMPOSITION		
FABRIC		100 % PES / 280 DTEX
TOTAL WEIGHT	DIN EN ISO 2286/2 1998	350 G/M ²
CHARACTERISTICS		ABUV
LACQUERING		1/1
EMBOSSING		LIN
BREAKING STRENGTH WARP	EN ISO 1421/1 1998	1100 N / 5 CM
BREAKING STRENGTH WEFT	EN ISO 1421/1 1998	1000 N / 5 CM
TEAR STRENGTH WARP	ISO 4674/1A 2004	60 N
TEAR STRENGTH WEFT	ISO 4674/1A 2004	30 N
ADHESION	EN ISO 2411 2000	60 N / 5 CM
LIGHT FASTNESS (EXCEPT WHITE AND (HALF-)TRANSPARENT)	ISO 105 B02 1988	7 - 8
TEMPERATURE RESISTANCE	DIN EN 1876/2 1998	-30/+70 °C
FIRE BEHAVIOR	ISO 3795 1989	< 100 MM/MIN
APPLICATION		CAMPING / MUDFLAP / SIDE-WALLS

All our technical characteristics are indicative.

⊕ THIS IS NOT A STANDARD PRODUCT. - MIN. 2000 LM.



1628 - 150 CM



1696 - 150 CM



5189 - 150 CM



5265 - 150 CM



6342 - 150 CM



7073 - 150 CM



7195 - 150 CM



7212 - 150 CM



7999 - 150 CM