

# CAMPING • C2421

LIST OF PROPERTIES		C2421
<b>MATERIAL COMPOSITION</b>		
FABRIC		100 % PES / 280 DTEX
TOTAL WEIGHT	DIN EN ISO 2286/2 1998	420 G/M <sup>2</sup>
CHARACTERISTICS		ABUV / OPQ
LACQUERING		1/1
EMBOSSING		DULL
BREAKING STRENGTH WARP	EN ISO 1421/1 1998	1100 N / 5 CM
BREAKING STRENGTH WEFT	EN ISO 1421/1 1998	1000 N / 5 CM
TEAR STRENGTH WARP	ISO 4674/1A 2004	60 N
TEAR STRENGTH WEFT	ISO 4674/1A 2004	30 N
ADHESION	EN ISO 2411 2000	60 N / 5 CM
TEMPERATURE RESISTANCE	DIN EN 1876/2 1998	-30/+70 °C
LIGHT FASTNESS (EXCEPT WHITE AND (HALF-)TRANSPARENT)	ISO 105 B02 1988	7 - 8
FIRE BEHAVIOR	ISO 3795 1989	< 100 MM/MIN
APPLICATION		ROOF / REGULAR

All our technical characteristics are indicative.



5041 – 150 CM



7214 – 150 CM



7215 – 150 CM