



CLEAN & CARE INSTRUCTIONS

CLEANING AND CARE OF PU-COATED FABRICS

WASH

WASHING

Washing (95°C) must be done with neutral detergents; softening agents are not allowed. Undyed fabrics may be washed following the ISO 6330 norm, part 9A and dyed fabrics following the ISO 6330 norm, part 3A.



DISINFECTION

In general our PU-coated products resist very well to alcohol-based disinfectants. Phenol or phenol derivatives can also be used in diluted concentrations (follow the recommendations of the disinfectant manufacturer). Nevertheless, we always advise to test the concerning product before using it. High concentrations of active chlorine might have a negative effect on our PU-coated fabrics. Hence, its use is not recommended. If one does decide to use it, please use strongly diluted concentrations and rinse the cover extensively with water. The same is valid for peroxide-based disinfectants, and, in general, all disinfectants based on an oxidising reaction mechanism. A study of several surface disinfectants is available upon your request. Sterilisation might have a negative effect on polyurethane coatings and is therefore not recommended. If one does decide to do so, a reduced lifetime of the product should be taken into account. This is inevitable for all thermoplastic polyurethanes, due to their chemical nature.

DRY

DRYING

Adequate drying is a crucial factor in the care and maintenance of coated articles. Drying may be effected by hanging out, spinning or tumbling at temperatures up to 60°C. Do not press or mangle.

STORE

STORAGE

Store in a dry area, at room temperature. Avoid excessive pressure and contact with non-colourfast materials. Try not to expose the PU-coating to excessive sunlight (UV-radiation).

CLEANING AND CARE OF PVC-COATED FABRICS

WASH

WASHING

Washing (40°C or 95°C) must be done with neutral detergents; softening agents are not allowed. Undyed fabrics may be washed following the ISO 6330 norm, part 9A and dyed fabrics following the ISO 6330 norm, part 3A.



DISINFECTION

In general, the PVC-coated products resist well to most of the currently used surface disinfectants. Nevertheless, we advise to test the particular surface disinfectant in advance or to contact us in case of doubts. It is not recommended to autoclave or sterilise PVC-coated products.

DRY

DRYING

Adequate drying is a crucial factor in the care and maintenance of coated articles. Drying may be effected by hanging out, spinning or tumbling at temperatures up to 60°C. Do not press or mangle.

STORE

STORAGE

Store in a dry area, at room temperature. Avoid excessive pressure and contact with non-colourfast materials. Try not to expose the PVC-coating to excessive sunlight (UV-radiation).



FOR MORE INFORMATION CHECK OUR WEBSITE
WWW.SIOEN.COM/FABRICSCOATING

CLEANING AND CARE OF "BRAVO EXCEL" & "SIOEN CARE" FABRICS

WASH

WASHING

Washing (95°C) must be done with neutral detergents; softening agents are not allowed. Undyed fabrics may be washed following the ISO 6330 norm, part 9A and dyed fabrics following the ISO 6330 norm, part 3A. Bravo Excel coatings can easily be washed > 100 times at 95°C (excluding possible physical damage of the coating due to contact with sharp metal parts in the washing machine).



DISINFECTION

In general, Bravo Excel coatings resist extremely well to all kinds of disinfectants. Nevertheless, we advise to test the particular surface disinfectant in advance or to contact us in case of doubts. Generally, surface wiping can be done numerous times without problems with the following commonly used products:

- Alcohol based disinfectants
- Phenol based disinfectants
- Disinfectants based on quaternary ammonium
- Active chlorine based disinfectants (> 100 times 5000 ppm)
Please always keep in mind to rinse the cover extensively with pure water after using chlorine.
- Chloramine based disinfectants
- Peroxyde based disinfectants



STERILISATION/AUTOCLAUVATION

Bravo Excel coatings have the best possible resistance against autoclave sterilisation. They have been tested and approved after 50 cycles autoclave at 134°C.

DRY

DRYING

Adequate drying is a crucial factor in the care and maintenance of coated articles. Drying may be effected by hanging out, spinning or tumbling at temperatures up to 130°C (inlet temperature hot air). Bravo Excel coatings have been tested and approved after 50 cycles tumbler drying at 130°C. Do not press or mangle.

STORE

STORAGE

Store in a dry area, at room temperature. Avoid excessive pressure and contact with non-colourfast materials. Try not to expose the PU excel coating to excessive sunlight (UV-radiation).



ADDING + TO YOUR LIFE



CAPACITY, FLEXIBILITY AND LARGE PRODUCT PORTFOLIO

We master 5 coating techniques; we have over 250 weaving looms; we have 10 coating lines; our own spinning mill, 30 plants in 14 countries, we master the entire pigment paste production process, we market over 30 000 products.

- 1** OUR QUALITY & SERVICE FLEXIBILITY:
OUR STRENGTHS = YOUR GUARANTEE.
- 2** OUR TEAM:
PEOPLE MAKE THE DIFFERENCE.
- 3** OUR PRODUCTION PLANTS:
WE CONSTANTLY INVEST IN KEEPING ALL OUR
FACTORIES STATE-OF-THE ART

“55 years

With over 55 years in the business, we have more accumulated know-how of textile coating technology and coated textile applications than any other company in the world. ”

DEDICATED R&D CUSTOMIZED DEVELOPMENT

At our central research and development center, our dedicated team of professionals makes specialised technical textiles their daily business. Our new ranges, with new and exclusive yarn formulations, techniques and lacquering, the result of intensified collaboration between our researchers, external specialists, universities.



SIOEN FABRICS

Z. I. DU BLANC BALLOT | AVENUE URBINO 6 | B-7700 MOUSCRON | BELGIUM | T +32 56 85 68 80 | F +32 56 34 61 31 | SIOENFABRICS@SIOEN.BE

FA
BRICS
COATING