

# ASPHALT • S9350

LIST OF PROPERTIES		S9350
<b>MATERIAL COMPOSITION</b>		
<b>FABRIC</b>		100 % PES / 1100 DTEX
<b>CHARACTERISTICS</b>		SILICONE COATED PES
<b>TOTAL WEIGHT</b>	DIN EN ISO 2286/2 1998	350 G/M <sup>2</sup>
<b>FEATURE</b>		FLUOR LACQUERED / UV
<b>LACQUERING</b>		1/1
<b>EMBOSSING</b>		DULL
<b>BREAKING STRENGTH WARP</b>	EN ISO 1421/1 1998	3000 N / 5 CM
<b>BREAKING STRENGTH WEFT</b>	EN ISO 1421/1 1998	2800 N / 5 CM
<b>TEAR STRENGTH WARP</b>	DIN 53363 2003	500 N
<b>TEAR STRENGTH WEFT</b>	DIN 53363 2003	500 N
<b>ADHESION</b>	EN ISO 2411 2000	
<b>TEMPERATURE RESISTANCE</b>	DIN EN 1876/2 1998	-50/+180 °C
<b>LIGHT FASTNESS (EXCEPT WHITE AND (HALF-)TRANSPARENT)</b>	ISO 105 B02 1988	7 - 8
<b>FIRE BEHAVIOR</b>	NF P 92 507 2004	M2
<b>APPLICATION</b>		TRUCK / ROLLOVER TARP / ASPHALT

All our technical characteristics are indicative