

• B6060 •



Fabric		100% PES 1100 dtex	
Thickness		0,93 [+/-10%] mm	DIN EN ISO 2286-3
Weight		1150 g/m ²	DIN EN ISO 2286-2
Characteristics		ABUV	
Lacquering		1/1	
Embossing		Dull	
Breaking strength	Warp	3800 N/5cm	EN ISO 1421-1
	Weft	3500 N/5cm	
Tear strength	Warp	550 N	DIN 53 363
	Weft	500 N	
Adhesion		100 N/5cm	EN ISO 2411
Gas permeability		< 400 cm ³ / m ² .bar.d	DIN 53 380
Temperature resistance		-30/+70°C	DIN EN 1876-2
Light fastness (Except white and (half-) transparent)		7-8	ISO 105 B02
Fire behavior		<100 mm/min	ISO 3795
Dimensional stability	Warp	< 0,5 %	10 MIN /100°C
	Weft	< 0,5 %	
Application		KIWA-manure-covers and liners	
KIWA (col.6158/6225/7264)		Conform	

COLOR RAL WIDTH (cm)

		300	
■ 7264	-		■ S
■ 6225	6021		■ NS
■ 6158	-		■ NS

S=STANDARD - NS=This is not a standard product.
Only on request. Minimum 1.000LM