

# • B9060 •



Fabric		100% PES 1100 dtex	
Weight		900 g/m <sup>2</sup>	DIN EN ISO 2286-2
Thickness		0,7 [+/-10%]mm	DIN EN ISO 2286-3
Characteristics		ABUV	
Lacquering		1/1	
Embossing		Dull	
Breaking strength	Warp	3000 N/5cm	EN ISO 1421-1
	Weft	2800 N/5cm	
Tear strength	Warp	300 N	DIN 53 363
	Weft	300 N	
Adhesion		100 N/5cm	EN ISO 2411
Gas permeability		< 400 cm <sup>3</sup> / m <sup>2</sup> .bar.d	DIN 53 380
Temperature resistance		-30°C/+70°C	DIN EN 1876-2
Light fastness(Except white and (half-) transparent)		7-8	ISO 105 B02
Fire behavior		<100 mm/min	ISO 3795
Dimensional stability	Warp	< 0,5 %	10 MIN /100°C
	Weft	< 0,5 %	
Application		KIWA-manure-covers	
KIWA (col.6158/6225/7264)		Conform	

COLOR	RAL	WIDTH (cm)
		300
■ 7264	-	■ S
■ 6225	6021	■ NS
■ 6158	-	■ NS

S=STANDARD

- NS=This is not a standard product.  
Only on request. Minimum 1.000LM