

LIST OF PROPERTIES	
S7667	
	MATERIAL COMPOSITION
100 % PES / 1100 DTEX	FABRIC
670 G/M ²	TOTAL WEIGHT DIN EN ISO 2286/2 1998
1-Z / AB	CHARACTERISTICS
1/-	LACQUERING
DP	EMBOSSING
2500 N / 5CM	BREAKING STRENGTH WARP EN ISO 1421/1 1998
1800 N /5CM	BREAKING STRENGTH WEFT EN ISO 1421/1 1998
250 N	TEAR STRENGTH WARP DIN 53363 2003
250 N	TEAR STRENGTH WEFT DIN 53363 2003
90 N / 5 CM	ADHESION EN ISO 2411 2000
-30/+70 °C	TEMPERATURE RESISTANCE DIN EN 1876/2 1998
7 - 8	LIGHT FASTNESS (EXCEPT WHITE AND (HALF-)TRANSPARENT ISO 105 B02 1988
< 100 MM/MIN	FIRE BEHAVIOR ISO 3795 1989
GROUNDSHEET / FLOORING	APPLICATION

All our technical characteristics are indicative.

