

• S5350 •

FOR EXTREME
TEMPERATURES:
-60°C:180°C
(SILICON)

This not a standard product.
Only on request. Minimum 3.000LM

| | | | |
|------------------------|--|---------------------------|----------------------|
| Fabric | | 100% PES 1100 dtex | |
| Weight | | 550 g/m ² | DIN EN ISO 2286-2 |
| Characteristics | | | |
| Lacquering | | -/- | |
| Embossing | | DP | |
| Breaking strength | Warp | 2200 N/5cm | EN ISO 1421-1 |
| | Weft | 2700 N/5cm | |
| Tear strength | Warp | 300 N | DIN 53 363 |
| | Weft | 600 N | |
| Adhesion | | 45 N/5cm | EN ISO 2411 |
| Temperature resistance | | -30/+70°C | DIN EN 1876-2 |
| Light fastness | (except white and (half-) transparent) | 7-8 | ISO 105 B02 |
| Fire behavior | | M2 | NFP 92 507 |
| Surface resistivity | | <3x10E08 Ohm | DIN 54345T1 |
| Application | | Industrial/ Miningduct | |

COLOR RAL WIDTH (cm)

■ 7999

-

■ 250

NS (min 10.000LM)