

• W20/20/3500 •

Fabric	Warp	100% PES - 280 dtex
	Weft	550 dtex
Weaving type		Leno
Weight		50 g/m ²
Construction	Warp	20
	Weft	20
Composition	Fabric	22 g/m ²
	Enduction	28 g/ m ² PVC
Lacquering		-/-
Breaking strength	Warp	360 N/5cm
	Weft	360 N/5cm
Shrinkage at 200°C/ 10minutes	Warp	-
	Weft	-
Elongation	Warp	>15%
	Weft	>15%
Adhesion		-
Temperature resistance		-30/+70°C
Light fastness	(except white)	-
Wind reduction		-
Flammability		M1
Application		Reinforcement for textile

For additional information and orders please contact Veranneman Technical Textiles on info@veranneman.be or T: 00 32 51 24 81 70

VERANNEMAN TECHNICAL TEXTILES