

# • W30/15/2320 •

FORMER  
M3102

Fabric	Warp	100% PES - 1100 dtex
	Weft	-
Weaving type		L 1:1
Weight		125 g/m <sup>2</sup>
Construction	Warp	30
	Weft	15
Composition	Fabric	50 g/m <sup>2</sup>
	Enduction	75 g/m <sup>2</sup> PVC
Lacquering		-/-
Breaking strength	Warp	1000 N/5cm
	Weft	500 N/5cm
Shrinkage at 200°C/ 10minutes	Warp	-
	Weft	-
Elongation	Warp	>15%
	Weft	>15%
Adhesion		25 N/5cm
Temperature resistance		-30/+70°C
Light fastness	(except white)	6-8
Wind reduction		20%
Flammability		-
Application		e.g. birdshields

COLOR	RAL	WIDTH (cm)
■ 6601	-	■ 210 S
■ 7999	-	■ S

S=STANDARD - NS=This is not a standard product.  
Only on request. Minimum 1.000LM