

## • W50/20/2000 •

Fabric	Warp	100% PES - 280 dtex
	Weft	100% PES - 280 dtex
Weaving type		L 1:1
Weight		55 g/m <sup>2</sup>
Construction	Warp	50
	Weft	20
Composition	Fabric	20 g/m <sup>2</sup>
	Enduction	35 g/ m <sup>2</sup> PVC
Lacquering		-/-
Breaking strength	Warp	420 N/5cm
	Weft	180 N/5cm
Shrinkage at 200°C/ 10minutes	Warp	<4,5%
	Weft	<3,5%
Elongation	Warp	>15%
	Weft	>15%
Adhesion		-
Temperature resistance		-30/+70°C
Light fastness	(except white)	-
Wind reduction		-
Flammability		M1
Application		Filtermedia reinforcement

For additional information and orders please contact Veranneman Technical Textiles on [info@veranneman.be](mailto:info@veranneman.be) or T: 00 32 51 24 81 70

**VERANNEMAN** TECHNICAL TEXTILES