

• W50/50/0690 •

FORMER
M5509

Fabric	Warp	100% PES - 1100 dtex
	Weft	-
Weaving type		L 1:1
Weight		250 g/m ²
Construction	Warp	50
	Weft	48
Composition	Fabric	110 g/m ²
	Enduction	140 g/ m ² PVC
Lacquering		-/-
Breaking strength	Warp	1800 N /5cm
	Weft	1600 N /5cm
Shrinkage at 200°C/ 10minutes	Warp	-
	Weft	-
Elongation	Warp	>15%
	Weft	>15%
Adhesion		40 N/5cm
Temperature resistance		-30/+70°C
Light fastness	(except white)	6-8
Wind reduction		90%
Flammability		-
Application		e.g. windshields

COLOR	RAL	WIDTH (cm)
		210
		320
1398	-	■ □ S
1399	-	■ □ S
3130	-	■ □ S
5601	-	■ □ S
6601	-	■ □ S
6602	-	■ □ S
7601	-	■ □ S
7999	-	■ □ S
8601	-	■ □ S
9917	-	■ □ S

S=STANDARD

- NS=This is not a standard product.
Only on request. Minimum 1.000LM