

• W50/50/1275 •

FORMER
M5508

Fabric	Warp	100% PES - 1100 dtex
	Weft	-
Weaving type		L 1:1
Weight		230g/m ²
Construction	Warp	50
	Weft	48
Composition	Fabric	110 g/m ²
	Enduction	120 g/ m ² PVC
Lacquering		-/-
Breaking strength	Warp	1800 N/5cm
	Weft	1600 N/5cm
Shrinkage at 200°C/ 10minutes	Warp	-
	Weft	-
Elongation	Warp	>15%
	Weft	>15%
Adhesion		35 N/5cm
Temperature resistance		-30/+70°C
Light fastness	(except white)	6-8
Wind reduction		75%
Flammability		-
Application		e.a. windshields

COLOR RAL WIDTH (cm)

■ 5601	-	210	■ S
■ 6601	-	360	■ S
■ 7999	-		■ S

S=STANDARD

- NS=This is not a standard product.
Only on request. Minimum 1.000LM