

• W50/95/11 •

FORMER
M5802

Fabric	Warp	100% PES - 1100 dtex
	Weft	-
Weaving type		L 1:1
Weight		350 g/m ²
Construction	Warp	50/95
	Weft	75
Composition	Fabric	160 g/m ²
	Enduction	190 g/m ² PVC
Lacquering		-/-
Breaking strength	Warp	2000 N/5cm
	Weft	2650 N/5cm
Shrinkage at 200°C/ 10minutes	Warp	-
	Weft	-
Elongation	Warp	>15%
	Weft	>15%
Adhesion		50 N/5cm
Temperature resistance		-30/+70°C
Light fastness	(except white)	6-8
Wind reduction		98%
Flammability		-
Application		e.g. windshields

COLOR	RAL	WIDTH (cm)
1399	-	210 S
6601	-	320 S
7999	-	S

S=STANDARD - NS=This is not a standard product.
Only on request. Minimum 1.000LM