• W60/60/5300 •

FORMER M6602

Fabric	Warp	100% PES - 1100 dtex
	Weft	-
Weaving type		L 1:1
Weight		280 g/m²
Construction	Warp	60
	Weft	58
Composition	Fabric	130 g/m²
	Enduction	150 g/m² PVC
Lacquering		-/-
Breaking strength	Warp	2000 N/5cm
Suchgui	Weft	1900 N/5cm
Shrinkage at 200°C/	Warp	-
10minutes	Weft	-
Elongation	Warp	>15%
	Weft	>15%
Adhesion		35 N/5cm
Temperature resistance		-30/+70°C
Light fastness	(except white)	6-8
Wind reduction		-
Flammability		-
Application		e.g. swimming pool-covers

S=STANDARD

NS=This is not a standard product.
Only on request. Minimum 1.000LM